


Somos® EvoLVe™ 128

Stereolithography

A resin offering durability and fast processing times.

Somos® EvoLVe 128 is a durable stereolithography material that produces accurate, high-detailed parts and has been designed for easy finishing. It has a look and feel that is almost indistinguishable from finished traditional thermoplastics, making it excellent for building parts and prototypes for functional testing applications – resulting in time, money and material savings during product development. Somos® EvoLVe is an excellent material for industries such as aerospace, automotive, medical, consumer products and electronics.



Key Benefits

- Easy to clean & finish
- High strength & durability
- Accurate & dimensionally stable
- High detail

Ideal Applications

- Tough, functional prototypes
- Snap-fit designs
- Jigs & fixtures

LIQUID PROPERTIES		OPTICAL PROPERTIES		
Appearance	Off-White	E_c	9.3 mJ/cm ²	[critical exposure]
Viscosity	~380 cps @ 30°C	D_p	4.3 mils	[slope of cure-depth vs. ln (E) curve]
Density	~1.12 g/cm ³ @ 25°C	E_{10}	95.1 mJ/cm ²	[exposure that gives 0.254 mm (.010 inch) thickness]

MECHANICAL PROPERTIES		UV POSTCURE	
ASTM	Property Description	Metric	Imperial
D638M	Tensile Modulus	2,964 MPa	430 ksi
D638M	Tensile Strength at Yield	56.8 MPa	8.2 ksi
D638M	Elongation at Break	11%	
D2240	Flexural Modulus	2,654 MPa	385 ksi
D256A	Izod Impact (notched)	38.9 J/m	0.729 ft-lb/in
D2240	Hardness (Shore D)	82	
D570-98	Water Absorption	0.4%	

THERMAL/ELECTRICAL PROPERTIES		UV POSTCURE	
ASTM	Property Description	Metric	Imperial
E831-05	C.T.E. 40°C – 0°C (-40°F – 32°F)	56.5 µm/m°C	31.4 µin/in°F
E831-05	C.T.E. 0°C – 50°C (32°F – 122°F)	76.5 µm/m°C	42.5 µin/in°F
E831-05	C.T.E. 50°C – 100°C (122°F – 212°F)	163 µm/m°C	90.8 µin/in°F
E831-05	C.T.E. 100°C – 150°C (212°F – 302°F)	174 µm/m°C	96.5 µin/in°F
D150-98	Dielectric Constant 60 Hz	4.3	
D150-98	Dielectric Constant 1KHz	3.7	
D150-98	Dielectric Constant 1MHz	3.5	
D149-97a	Dielectric Strength	31 kV/mm	788 V/mil
D648	HDT @ 0.46 MPa (66 psi)	52.3°C	126°F
D648	HDT @ 1.81 MPa (264 psi)	49.6°C	121°F

These values may vary and depend on individual machine processing and post-curing practices.

USA - Headquarters

7665 Commerce Way
Eden Prairie, MN 55344, USA
+1 952 937 3000

ISRAEL - Headquarters

1 Holtzman St., Science Park
PO Box 2496
Rehovot 76124, Israel
+972 74 745 4000

[stratasys.com](https://www.stratasys.com)

ISO 9001:2015 Certified

EMEA

Airport Boulevard B 120
77836 Rheinmünster, Germany
+49 7229 7772 0

ASIA PACIFIC

7th Floor, C-BONS International Center
108 Wai Yip Street Kwun Tong Kowloon
Hong Kong, China
+ 852 3944 8888



GET IN TOUCH.

www.stratasys.com/contact-us/locations

